## ATMY ANALYTICAL LABS PVT.LTD.



I-30, DLF Industrial Area, Phase-1, Faridabad (Haryana) INDIA Phone: +91-129-4019544 info@atmylabs.com, www.atmylabs.com

Testing

Research

Innovation

### TEST REPORT

Page 1 of 2
Report No.: 2008060061 Date: 17-08-2020

Issued To:

#### M/s GREENTECH UPVC INDIA PVT. LTD.

SY. NO. - 220-230, SAMPANBOLE VILLAGE, JAGANGUDA GP, SHAMIRPET MANDAL, MEDCHAL TELANGANA - 500078

Sample Description : GREENTECH UPVC PROFILE

Sample Received Date : 06-08-2020 Sample Drawn By : Client Specification : --

Test Requested : Fire resistance

Test Method : Refer to Attached Pages.
Test Result : Refer to Attached Pages.

#### SAMPLE PICTURE





#### Terms & Conditions:-

Sample will not be retained more than one month for chemical and three month for mechanical unless specified instructed.
 Sample analysis conducted on as received basis and followed by customer description unless specified otherwise.
 The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise.
 Any complaints matter about this report should be communicated in written, within 7 days of issue of this report.
 The result listed refer only to the tested samples and applicable parameters as described by customer.
 Endorsement of product is neither inferred nor implies.
 Total liability of our laboratory is limited to the invoiced amount only.
 This report cannot be used as an evidence in a court of law without the written approval of the laboratory.





# ATMY ANALYTICAL LABS PVT.LTD.



I-30, DLF Industrial Area, Phase-1, Faridabad (Haryana) INDIA Phone: +91-129-4019544 info@atmylabs.com, www.atmylabs.com

TestingResearch

Innovation

## TEST REPORT

Page 2 of 2
Report No.: 2008060061 Date: 17-08-2020

I. Physical Test

1.

Fire resistance Test Performed on: 08-08-2020 to 13-08-2020

Test Method: IS:4249

<u>Test</u> <u>Observation Data</u> <u>Result</u>

Fire Resistance Sample 1

**Condition:-** After removal of flame burn till 3 seconds. Self Extinguishing

Temp. - 27±2°C in nature.

Duration – 24 hours Sample 2

Humidity - 65±5 % After removal of flame burn till 4 seconds.

Specimen size:-

Length – 100 mm Sample 3

Width – 15 mm After removal of flame burn till 2 seconds.

-----End of Report-----



P.N.Rao SR. ANALYST

**Authorised Signatory** 







